



OAK CHALK

Oak Chalk is a gently white-colored oak floor, bringing the thoughts to the Mediterranean area with its white chalked stonewalls. This 3-strip, matt lacquered floor has a modern yet classic and timeless look.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	133B14EKLCKW226	Wood Species	Oak	Moisture	EN13183	7%±2%
EAN Code	7393969048415	Board	3-strip	content		
Surface treatment	Matt lacquer	Grading	Variation	Minimun Mean Density kg/m³ >500 kg/m³		
Dimensions	2266 x 188 x 13 mm	Range	Kährs Avanti	Reaction To Fire	EN13501-1	Dfl-s1
Weight per Package (kg)	24.55 kg	Collection	Ground Collection	Formaldehyde Emission	EN717-1	E1
Area per Package (m²)	3.41 m ²	Resandable	2-3 times			
Area per pallet (m²)	119.35 m ²	Natural/Stained	Stained	Content PCP	CEN/TR14823	3 ≤ 5 x 10-6n
Package info	Packages may contain start and stop boards.	Brinell Value	3,7	Breaking Strength N/mm²	EN1533	NPD
		Joint	Woodloc® 5G			
DETAIL DESCRIPTION		Floor heating	Yes	Thermal	EN12664	0,14 W/mK
Naturally occuring wood colour variations allowed, from light to dark brown. Sapwood will occur. The product includes small sound and black knots. Knots may vary in size and numbers. COLOUR CHANGE		Warranty	20 years	Conductivity		
		Wear-layer material	Hardwood	Thermal Resistance R-Value		.09 (m2K/W)
		Wear-layer thickness	2.6 mm	Biological Durability	EN350-2	Class 1
		Core material	Pine/Spruce lamella	CARB2		Compliant
		LRV	50			Compliant
${\it Stained product-noticeable color change over time.}$		Installation method	Floating, Glue-down			

















Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.